

Product Description

Chemical characterization	Controlled adjusted modified strontium aluminium polyphosphate hydrate
---------------------------	--

HEUCOPHOS® SRPP is a special adjustment of HEUCOPHOS® SAPP for the application, mainly in coil coatings and aircraft primers.

Technical Data

	Unit	Value	Test Method
Strontium as SrO	[%]	23.5 - 30.0	ICP-OES
Aluminium as Al ₂ O ₃	[%]	10.5 - 13.5	Complexometric titration
Phosphorous as P ₂ O ₅	[%]	43.5 - 48.0	acc. to ISO 6745
Water-soluble chloride	[%]	max. 0.025	acc. to ISO 787-13
Water-soluble sulphate	[%]	max. 0.05	acc. to ISO 787-13
Lead as Pb	[ppm]	max. 10	ICP-OES
Cadmium as Cd	[ppm]	max. 10	ICP-OES
Loss on ignition 600 °C	[%]	9.5 - 15.0	acc. to ISO 6745
Conductivity	[µS/cm]	max. 1500	acc. to ISO 787-14
pH value		4.0 - 6.0	acc. to ISO 787-9
Density	[g/cm ³]	typ. 2.8	acc. to ISO 787-10
Bulk density	[g/cm ³]	typ. 0.4	
Tamped density	[g/cm ³]	typ. 0.7	acc. to ISO 787-11
Oil absorption	[g/100g]	typ. 40	acc. to ISO 787-5
Sieve residue 32 µm	[%]	max. 0.01	acc. to ISO 787-7
Average particle size	[µm]	2.0 - 3.5	acc. to ISO 13319

Tds-ac_srpp-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.

Application Profile			
Solvent based coatings			
Short and medium oil alkyds			
Long oil alkyds			
High solids alkyds		✓	
2K Epoxies	++		
Epoxy esters			
High solids epoxies		✓	
2K Polyurethanes	++		
High solids polyurethanes	++	✓	
Moisture cured polyurethanes			
Silicone resins			
Water based coatings			
Alkyd emulsions		✓	
2K Epoxies	+	✓	
1K Polyurethanes		✓	
2K Polyurethanes	+	✓	
Silicone resins		✓	
Acrylic and modified acrylics		✓	
Butadiens		✓	
Specialty coatings			
Coil coatings	+++		●
Aircraft primers	+++		●
Wash and shop primers			
Direct to metal			
UV cured systems		✓	
Powder coatings		✓	

+++ Excellent choice

++ Good choice

+ Possible choice

✓ Resin with low or no VOCs

● Additionally recommended in combination with HEUCORIN® RZ

Tds-ac_srpp-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.