

# Calcium Phosphate CP

In polyurethane



Solvent based

Heubach formulation No. 06291

08/06

FUNCTION	PRODUCT	PRODUCER	PBW
<b>Component A</b>			
Acrylic	Desmophen A 160, 60%	Bayer	37.70
Solvent	Butyl acetate		5.45
Solvent	Methoxypropyl acetate		5.45
Wetting and Dispersing agent	Anti-Terra-204	Byk-Chemie	0.56
Rheology modifier	Rilanit Spezial Micro paste, 10% in Xylene	Cognis	6.60
<b>Premix.</b>			
Antisettling agent	Aerosil R 972	Degussa, today Evonik	0.33
Magnesium silicate	Finntalc M15	Mondo Minerals	10.70
Calcium carbonate	Millicarb	Omya	9.20
Titanium dioxide	Kemira 660	Kemira	7.80
Anticorrosive pigment	Calcium Phosphate CP	Heubach	9.80
Carbon black	Flammruß 101	Degussa, today Evonik	0.01
<b>Grind.</b>			<b>93.60</b>
<b>Component B</b>			
Curing agent	Desmodur N 3390, 90%	Bayer	6.40
<b>Add.</b>			<b>6.40</b>
<b>Mix components A and B thoroughly prior to use.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
PVC / CPVC			0.6
Solids in %			67.2
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0

# Calcium Phosphate CP

In polyurethane



*Solvent based*

Heubach formulation No. 06291

08/06

## SPECIFICATIONS

PVC in %

33.4

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.