

FUNCTION	PRODUCT	PRODUCER	PBW
Component A			
Epoxy	Araldite GT 6071, 60% in Xylene	Huntsman	18.30
Aromatic hydrocarbon	Xylene		9.60
Wetting agent	Soya lecithine		0.30
Glycol ether	Dowanol PMA	CG Chemikalien	3.20
Premix.			
Anticorrosive pigment	HEUCOPHOS® SRPP	Heubach	13.20
Corrosion inhibitor	HEUCORIN® RZ	Heubach	1.50
Titanium dioxide	Kemira 650	Kemira	3.40
Barium sulphate	Albaryt	Sachtleben	4.90
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	7.60
Iron oxide yellow	Bayferrox 3920	Bayer	4.50
Iron oxide red	Bayferrox 130 M	Bayer	0.10
Rheology modifier	Bentone SD-1	Elementis	0.60
Grind with a bead mill.			
Epoxy	Araldite GT 6071, 60% in Xylene	Huntsman	9.10
Glycol ether	Dowanol PMA	CG Chemikalien	4.50
Add while mixing.			80.80
Component B			
Curing agent	Aradur 3776XW55	Huntsman	10.95
Solvent	N-Butyl alcohol		1.20
Solvent	N-Propyl alcohol		1.35
Solvent	Solvesso 100	Exxon	2.85
Glycol ether	Dowanol PM	CG Chemikalien	2.85

HEUCOPHOS[®] SRPP / HEUCORIN[®] RZ

in aircraft primer



Solvent based

Heubach formulation No. 410-12

10/07

FUNCTION	PRODUCT	PRODUCER	PBW
Mix.			
			19.20
Mix components A and B thoroughly prior to use.			
			100.00
SPECIFICATIONS			
CPVC			45.0
PVC / CPVC			0.8
PVC in %			36.0
Vol.-% Anticorrosive pigment reg. pigment/filler			47.0

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.