

HEUCOPHOS® ZCP-PLUS

in styrene-acrylic dispersion



Water based

Heubach formulation No. 09312

04/09

FUNCTION	PRODUCT	PRODUCER	PBW
Styrene-acrylic dispersion	Lipaton X 6030, 50%	Polymer Latex	55.40
Defoamer	Bevaloid 681 F	Erbslöh	0.30
Glycol ether	Butyl glycol		4.00
Wetting agent	Lutensit A-EP	BASF	0.30
Premix, adjust pH 9.0 with ammonia, 25%.			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	12.00
Calcium carbonate	Millicarb OG	Omya	6.00
Magnesium silicate	Mistron 754	Talc de Luzenac	4.00
Iron oxide red	Bayferrox 222 FM	Lanxess	15.00
PU-thickener	Ser-AD FX 1010, 10% in H ₂ O	Elementis	1.10
Grind with a bead mill.			
Defoamer	Bevaloid 681 F	Erbslöh	0.40
Flash-rust inhibitor	Corrosion inhibitor L 1	Erbslöh	0.50
Solvent	White spirit		1.00
Add to the grind. Adjust pH 9.0 with ammonia, 25%.			
			100.00
SPECIFICATIONS			
Vol.-% Anticorrosive pigment reg. pigment/filler			34.0
PVC in %			29.0
Solids in %			66.1

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.