

Heubach formulation No. 02238

04/02

FUNCTION	PRODUCT	PRODUCER	PBW
Styrene-acrylic	Pliolite Ac4, 100%	Goodyear	8.60
Styrene-acrylic	Pliolite Ac80, 100%	Goodyear	7.90
Polyester	Haftharz LTH	Degussa, today Evonik	1.20
Plasticizer	Resamin HF 450	Cytec	1.50
Premix.			
Titanium dioxide	Tioxide TR 92	Huntsman	7.10
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	23.60
Magnesium silicate	Micro-Talc A.T. Extra	Mondo Minerals	5.90
Grind.			
Solvent	White spirit 100-160		27.70
Solvent	Solvesso 100	Exxon	16.50
Add while mixing.			
			100.00

* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.