

## Nyco Minerals formulation

10/99

FUNCTION	PRODUCT	PRODUCER	PBW
Antisettling agent	M-P-A 1078	NL Industries, today Elementis	0.75
High solids alkyd	Aroplaz 3786-M-90	Spencer Kolleg, today Reichhold	27.85
Dispersing agent	Nuosperse 657	Hüls, today Elementis	0.40
<b>Premix.</b>			
Iron oxide red	Red Iron Oxide 3108	Mineral Pigments, today Rockwood	14.40
Calcium metasilicate	10 AS Wollastocoat	Nyco Minerals	19.20
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	24.45
Rheology modifier	Bentone SD-1	NL Industries, today Elementis	0.15
<b>Grind.</b>			
Solvent	White spirit		11.40
Drier	Cobalt Chem-All 12%	Mooney Chemicals	0.20
Drier	Calcium Chem-All 8%	Mooney Chemicals	0.70
Drier	Zirconium Chem-All 12%	Mooney Chemicals	0.35
Antiskinning agent	Skino #1	Mooney Chemicals	0.15
<b>Add components separately while mixing.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			41.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.