



Product Description

HEUCO®FIT LR is a pigment preparation of inorganic and/or organic pigments and extenders. HEUCO®FIT LR Yellow 1007002 is a red shade yellow with excellent opacity and high tinting strength. Due to its brilliant and clean color shade it can be used as a direct replacement of lead chromate pigments. This economic pigment preparation is designed for full shade applications.

Appearance	Yellow powder
------------	---------------

Technical Data

	Unit	Value	Test Method
Density	[g/cm ³]	typ. 2.6	acc. to ISO 787-10
Bulk volume	[l/kg]	typ. 3.7	
Oil absorption	[g/100g]	typ. 24	acc. to ISO 787-5

Fastness Properties

Resistance to Chemicals

	Value	Test Method
Acid	5	rating acc. to DIN EN ISO 105-A03
Alkali	5	rating acc. to DIN EN ISO 105-A03

Acid/alkali resistance: Product was dipped into hydrochloric acid (10%) or soda solution (10%). Rating with gray scale: 1=poor, 5=excellent.

	Value	Test Method
Overpainting fastness	4	rating acc. to DIN EN ISO 105-A03
Heat resistance [°C]	150	acc. to DIN EN 12877-2
Weather fastness [full shade]	4 - 5	acc. to DIN EN ISO 16474-2/DIN EN ISO 20105-A02

Overpainting: Tested in 2K acrylic system with 30 minutes baking time at 80 °C. Rating with gray scale: 1=poor, 5=excellent.

Heat resistance: Tested in 2K acrylic system.

Weather fastness: Tested in water based automotive system. Rating with gray scale after 2000 h accelerated weathering: 1=poor, 5=excellent.

Tds-hf_y1007002-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.

Application Profile

Automotive coatings	
General industrial coatings	+++
Coil coatings	
Powder coatings	
Decorative coatings	+++
Plastics	

+++ Excellent choice

++ Good choice

+ Possible choice

Packaging and Handling

Packaging	15 kg paper bags
-----------	------------------

Safety

Product contains diarylide pigments. These pigments should not be used at processing temperatures exceeding 200 °C due to potential cleavage to 3,3'-dichlorobenzidine (DCB) under these conditions.

Tds-hf_y1007002-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.