

Heubach formulation No. 99168

11/99

FUNCTION	PRODUCT	PRODUCER	PBW
Alkyd emulsion	WorléeSol E 440 W, 40%	Worlée	20.00
Dispersing agent	Disperbyk-190	Byk-Chemie	1.00
Defoamer	Tego Foamex 815	Tego Chemie	0.20
<b>Premix.</b>			
Titanium dioxide	Kemira 650	Kemira	10.10
Carbon black	Flammruß 101	Degussa, today Evonik	0.05
Magnesium silicate	Talk Naintsch ST-20	Naintsch, today Luzenac	4.10
Magnesium calcium carbonate	Microdol Super	Mondo Minerals	10.40
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	7.30
Antisettling agent	Aerosil 300	Degussa, today Evonik	0.20
<b>Grind.</b>			
	Water		3.00
Alkyd emulsion	WorléeSol E 440 W, 40%	Worlée	41.95
Drier	Additol VXW 4940, 50% in H <sub>2</sub> O	Vianova Resins, today Cytec	1.70
<b>Add to the grind. Adjust pH 7.5 - 8.5 with ammonia.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Solids in %			57.8
Vol.-% Anticorrosive pigment reg. pigment/filler			20.3

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.