

Hüls formulation No. Wa 3401 / today Evonik

11/95

FUNCTION	PRODUCT	PRODUCER	PBW
Polyester	Dynapol LH 833-03, 50%	Hüls, today Evonik	40.00
Antisettling agent	Aerosil 200	Degussa, today Evonik	0.40
Titanium dioxide	Kronos 2059	Kronos	10.20
Anticorrosive pigment	HEUCOPHOS® SAPP	Heubach	7.40
Solvent	Solvesso 150	Exxon	9.00
<b>Grind with a bead mill, fineness of grind &lt; 15 microns.</b>			
Polyester	Dynapol LH 833-03, 50%	Hüls, today Evonik	8.00
Blocked isocyanate	Desmodur BL 3175, 75%	Bayer	5.60
Melamine resin	Cymel 325, 80%	Dyno Cyanamid, today Cytec	3.60
Epoxy	Epikote 1004, 50% in Methoxypropyl acetate	Shell, today Hexion	5.60
Catalyst	Dabco T-12CL	Air Products	0.20
Solvent	Methoxypropyl acetate		3.00
Solvent	Solvesso 100	Exxon	7.00
<b>Add.</b>			
			<b>100.00</b>
<b>SPECIFICATIONS</b>			
Solids in %			52.0

\* = Registered trademark of Heubach GmbH. Our product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.