



| Product Description | |
|---------------------------|--------------------|
| Chemical characterization | Benzimidazolone |
| Color Index | Pigment Yellow 154 |
| Appearance | Yellow powder |
| C.I. No. | 11781 |
| CAS No. | 68134-22-5 |

| Product Description | | | |
|------------------------|------|-------|--------------------------------|
| | Unit | Value | Test Method |
| Hue angle [1/3 SD] | | 88.8 | acc. to DIN EN ISO/CIE 11664-4 |
| 1/3 SD reduction ratio | | 1:1.8 | acc. to DIN 53235-2 |

| Technical Data | | | |
|------------------|----------------------|-----------|-----------------------|
| | Unit | Value | Test Method |
| Density | [g/cm ³] | typ. 1.5 | acc. to ISO 787-10 |
| Bulk volume | [l/kg] | typ. 2.3 | |
| Specific surface | [m ² /g] | typ. 11.0 | acc. to DIN ISO 66132 |
| Oil absorption | [g/100g] | typ. 51 | acc. to ISO 787-5 |

| Fastness Properties | | |
|-------------------------|-------|-----------------------------------|
| Resistance to Chemicals | | |
| | Value | Test Method |
| Acid | 5 | rating acc. to DIN EN ISO 105-A03 |
| Alkali | 5 | rating acc. to DIN EN ISO 105-A03 |
| Water | 5 | rating acc. to DIN EN ISO 105-A03 |
| Butanol | 4 | rating acc. to DIN EN ISO 105-A03 |
| Butylacetate | 5 | rating acc. to DIN EN ISO 105-A03 |
| Xylene | 5 | rating acc. to DIN EN ISO 105-A03 |
| MEK | 4 - 5 | rating acc. to DIN EN ISO 105-A03 |
| White spirits | 4 - 5 | rating acc. to DIN EN ISO 105-A03 |

Acid/alkali resistance: Pigment was dipped into hydrochloric acid (10%) or soda solution (10%). Rating with gray scale: 1=poor, 5=excellent.

Solvent resistance: Pigment was dipped into solvent. Rating with gray scale: 1=poor, 5=excellent.

Tds-ml_y115401-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.

| | Value | Test Method |
|-----------------------------|-------|---|
| Overpainting fastness | 4 - 5 | rating acc. to DIN EN ISO 105-A03 |
| Heat resistance [°C] | 160 | acc. to ISO 787-21 |
| Light fastness [full shade] | 8 | acc. to DIN EN ISO 16474-2/DIN EN ISO 105-B02 |
| Light fastness [1/3 SD] | 8 | acc. to DIN EN ISO 16474-2/DIN EN ISO 105-B02 |

Overpainting: Tested in alkyd/melamine system with 30 minutes baking time at 160 °C. Rating with gray scale: 1=poor, 5=excellent.

Heat resistance: Tested in alkyd/melamine system.

Light Fastness: Tested in water based automotive system. Rating with 8-step wool scale: 1=poor, 8=excellent.

| Weather Fastness | | |
|------------------|------------|--------|
| | Full Shade | 1/3 SD |
| 1600 h | 5 | 5 |
| 3200 h | 5 | 5 |
| 4800 h | 5 | 4 - 5 |

Tested acc. to DIN EN ISO 16474-2 in water based automotive system. Rating with gray scale in acc. to DIN EN ISO 20105-A02: 1=poor, 5=excellent.

| Application Profile | |
|---------------------|-----|
| Automotive coatings | +++ |
| Industrial coatings | +++ |
| Decorative coatings | +++ |
| Coil coatings | |
| Powder coatings | +++ |

+++ Excellent choice ++ Good choice + Possible choice

| Packaging and Handling | |
|------------------------|--|
| Packaging | 20 kg cardboard boxes |
| Packaging | Different types of packaging are available on request. |

Tds-ml_y115401-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.