

in Short oil alkyd

Solvent based coatings

Allnex formulation No. HM 10/1

Rev. Number: 01.01

02/00

Function	Product	Producer	PBW
Short oil alkyd	VIALKYD® AF 342n/60X	Allnex	37.60
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	8.80
Iron oxide red pigment	BAYFERROX® 130	LANXESS	11.20
Magnesium silicate	Microtalc™ IT Extra	Elementis	15.70
Calcium carbonate	Millicarb®	Omya	8.80
Wetting and antissettling agent	ADDITOL® XL 280	Allnex	2.30
Grind.			
Antiskinning agent	ADDITOL® XL 297	Allnex	0.50
Drier	Octa-Soligen® 173	Borchers	1.40
Solvent	Xylene		13.70

Add components separately while stirring.

100.00

Specifications

Solids in %	67.0
-------------	------

Gf-SB01_001-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.