

in Short oil alkyd

Solvent based coatings

DSM Coating Resins formulation No. AM06021

Rev. Number: 01.01

01/06

Function	Product	Producer	PBW
Phenolic modified short oil alkyd	Uralac® AM351 X-50	DSM Coating Resins	20.90
Rheology modifier	BENTONE® 38, 10% in Xylene/Ethanol	Elementis	2.50
Wetting agent	NUOSPERSE® FA 601	Elementis	0.65
Anticorrosive pigment	HEUCOPHOS® ZAPP	Heubach	12.00
Magnesium silicate	Microtalc™ IT Extra	Elementis	4.00
Barium sulfate	BLANC FIXE micro®	Venator	10.00
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	7.00
Add while stirring.			
Phenolic modified short oil alkyd	Uralac® AM351 X-50	DSM Coating Resins	29.20
Drier	Durham Nuodex® Calcium 10	Venator	0.65
Drier	Durham Nuodex® Cobalt 10	Venator	0.10
Drier	Durham Nuodex® Zirconium 12	Venator	0.85
Antiskinning agent	Exkin® 2	Venator	0.25
Solvent	Xylene		11.90
Grind at high speed.			
			100.00
Specifications			
PVC in %			27.0
Solids in %			59.1

Gf-SB01_008-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.