

in Short oil alkyd

Solvent based coatings

DSM Coating Resins formulation No. AK06029

Rev. Number: 01.01

02/06

Function	Product	Producer	PBW
Short oil alkyd	Uralac® AK424 X-60	DSM Coating Resins	16.50
Solvent	Xylene		2.00
Drier	Durham Nuodex® Calcium 5	Venator	0.40
Wetting agent	NUOSPERSE® FA 601	Elementis	0.70
Anticorrosive pigment	HEUCOPHOS® ZAPP	Heubach	10.50
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	9.50
Magnesium silicate	Microtalc™ IT Extra	Elementis	8.50
Barium sulfate	BLANC FIXE micro®	Venator	10.00
Rheology modifier	BENTONE® SD-1	Elementis	0.15
Grind at high speed.			
Short oil alkyd	Uralac® AK424 X-60	DSM Coating Resins	27.00
Drier	Durham Nuodex® Cobalt 10	Venator	0.05
Drier	Durham Nuodex® Zirconium 12	Venator	0.45
Antiskinning agent	Exkin® 2	Venator	0.25
Solvent	Xylene		14.00
Add while stirring.			
			100.00
Specifications			
PVC in %			33.1
Solids in %			65.2

Gf-SB01_009-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.