

in Short oil alkyd

Solvent based coatings

Heubach formulation No. 299-02

Rev. Number: 01.01

07/07

Function	Product	Producer	PBW
Short oil alkyd	VIALKYD® AF 342n/60X	Allnex	34.55
Solvent	Xylene		18.55
Rheology modifier	BENTONE® SD-3	Elementis	0.40
Drier	Octa-Soligen® Calcium 10, basic	Borchers	0.10
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	10.15
Barium sulfate	Albasoft 70	Sachtleben Minerals	18.20
Magnesium silicate	FINNTALC M10	Elementis	10.75
Titanium dioxide	KRONOS® 2190	KRONOS	5.95
Grind.			
Drier	Octa-Soligen® 173	Borchers	1.10
Antiskinning agent	Borchi® Nox M2	Borchers	0.25
Add components separately while stirring.			

 100.00
Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	22.0
PVC in %	40.4
PVC / CPVC	0.7

Gf-SB01_012-01_01B

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.