

in Short oil alkyd

Solvent based coatings

Heubach formulation No. 751-09

Rev. Number: 01.01

07/14

Function	Product	Producer	PBW
Short oil alkyd	WorléeKyd SM 433	Worlée-Chemie	34.50
Solvent	Solvesso™ 100	ExxonMobil	22.10
Glycol ether	DOWANOL™ PM	Dow	2.00
Rheology modifier	AEROSIL® 300	Evonik	0.30
Premix.			
Solvent	Xylene		2.60
Rheology modifier	BENTONE® 38	Elementis	0.30
Wetting and dispersing agent	ANTI-TERRA®-204	BYK-Chemie	0.10
Mix until uniform paste prior to addition.			
Drier	Octa-Soligen® Calcium 10, basic	Borchers	0.45
Anticorrosive pigment	HEUCOPHOS® CAPP	Heubach	8.60
Titanium dioxide	KRONOS® 2190	KRONOS	4.65
Mica/quartz/chlorite filler	Plastorit® Micro	Imerys	4.65
Iron oxide black pigment	BAYFERROX® 318	LANXESS	0.45
Magnesium silicate	FINNTALC M15	Elementis	11.20
Calcium/Magnesium carbonate	MICRODOL® EXTRA	Omya	7.45
Grind with a bead mill.			
Drier	Octa-Soligen® Cobalt 6	Borchers	0.20
Drier	Octa-Soligen® Zirconium 12	Borchers	0.15
Antiskinning agent	Exkin® 2	Venator	0.30
Add components separately while stirring.			
			100.00

Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	25.0
PVC in %	41.1
PVC / CPVC	0.8
Solids in %	58.2

Gf-SB01_017-01_01B

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.