

in Medium oil alkyd

Solvent based coatings

Heubach formulation No. 350-07

Rev. Number: 01.01

06/04

Function	Product	Producer	PBW
Medium oil alkyd	Halweftal® B 53	DSM Coating Resins	44.50
Drier	Octa-Soligen® Calcium 4, basic	Borchers	0.40
Rheology modifier	RHEOTIX® 240	BYK-Chemie	1.30
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	8.00
Anticorrosive pigment	Zinc oxide		2.20
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	2.95
Carbon black pigment	Lamp black® 101	Orion Engineered Carbons	0.10
Mica/quartz/chlorite filler	Plastorit® Micro	Imerys	7.35
Talc/chlorite filler	LUZENAC 10M2	Imerys	3.65
Barium sulfate	Schwerspat C101	Sachtleben Minerals	13.90
Mix.			
Rheology modifier	TIXOGEL® MP 100	BYK-Chemie	0.50
Solvent	White Spirit (145-200 °C)		4.25
Solvent	Shellsol® A	Shell	5.10
Grind with a bead mill.			
Phenol/Formaldehyde resin	TUNGOPHEN® B NV	Allnex	0.80
Drier	Octa-Soligen® Cerium 10	Borchers	0.40
Solvent	Shellsol® A	Shell	3.95
Antiskinning agent	Ascinin® R	Borchers	0.65
Add while stirring.			
			100.00

Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	20.0
PVC in %	29.0
PVC / CPVC	0.5
Solids in %	63.0

Gf-SB01_024-01_01B

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.