

## in Long oil alkyd

Solvent based coatings

Heubach formulation No. 98141

Rev. Number: 01.01

08/98

Function	Product	Producer	PBW
Long oil alkyd	ETERKYD 1106-M-70-3	Eternal Materials	40.00
Rheology modifier	BENTONE® SD-3	Elementis	0.30
Solvent	White Spirit		8.40
Drier	Octa-Soligen® Calcium 10, basic	Borchers	0.30
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	9.00
Barium sulfate	Albasoft 70	Sachtleben Minerals	24.00
Magnesium silicate	FINNTALC M10	Elementis	10.00
Titanium dioxide	KRONOS® 2190	KRONOS	5.30
<b>Grind.</b>			
Drier	Octa-Soligen® 173	Borchers	2.40
Antiskinning agent	Borchi® Nox M2	Borchers	0.30
Add components separately while stirring.			

---



---

 100.00
**Specifications**

Vol.-% Anticorrosive pigment reg. pigment/filler	18.7
Solids in %	78.0

Gf-SB02\_001-01\_01B

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.