

in Long oil alkyd

Solvent based coatings

Heubach formulation No. 99151

Rev. Number: 01.01

08/99

Function	Product	Producer	PBW
Long oil alkyd	BECKOSOL® 10-060	Polynt	31.10
Submission.			
Solvent	White Spirit		14.30
Rheology modifier	BENTONE® 34	Elementis	1.00
Solvent	Methyl alcohol		0.20
Mix until uniform paste prior to addition.			
Iron oxide red pigment	BAYFERROX® 222 FM	LANXESS	7.20
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	9.60
Magnesium silicate	Beaverwhite 325	Imerys	23.90
Grind.			
Long oil alkyd	BECKOSOL® 10-060	Polynt	7.20
Solvent	White Spirit		4.30
Drier	Octa-Soligen® Zirconium 12	Borchers	0.30
Drier	Octa-Soligen® Cobalt 12	Borchers	0.10
Drier	Octa-Soligen® Zinc 8	Borchers	0.40
Drier	Octa-Soligen® Calcium 4, basic	Borchers	0.20
Antiskinning agent	Skino® #2	Borchers	0.20
Add components separately while stirring.			
			100.00

Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	23.4
PVC in %	37.2
Solids in %	68.9

Gf-SB02_003-01_01B

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.