

in High solid alkyd

Solvent based coatings

Heubach formulation No. 99153

Rev. Number: 01.01

08/99

Function	Product	Producer	PBW
Phenolic mod. medium oil alkyd	Rezamac® HS 57-5703	Polynt	16.50
Solvent	Butyl acetate		1.15
Premix.			
Rheology modifier	BENTONE® SD-2	Elementis	0.20
Iron oxide red pigment	BAYFERROX® 222 FM	LANXESS	20.65
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	8.00
Calcium carbonate	Snowflake® P.E.	Imerys	14.40
Magnesium silicate	Beaverwhite 325	Imerys	7.50
Solvent	Xylene		2.75
Grind.			
Phenolic mod. medium oil alkyd	Rezamac® HS 57-5703	Polynt	19.40
Solvent	Butyl acetate		7.20
Drier	Octa-Soligen® Cobalt 12	Borchers	0.10
Drier	Octa-Soligen® Zirconium 18	Borchers	0.45
Drier	Octa-Soligen® Calcium 10, basic	Borchers	0.15
Antiskinning agent	Skino® #2	Borchers	0.15
Solvent	Xylene		1.40

Add components separately while stirring.

 100.00
Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	15.0
--	------

Gf-SB03_001-01_01B

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.