

## in High solid alkyd

Solvent based coatings

Heubach formulation No. 99163

Rev. Number: 01.01

09/99

Function	Product	Producer	PBW
Medium oil alkyd	BECKOSOL® 6440-A4-85	Polynt	12.50
Titanium dioxide	Ti-Pure™ R-902+	The Chemours Company	22.30
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	10.00
Solvent	Xylene		6.00
<b>Grind.</b>			
Medium oil alkyd	BECKOSOL® 6440-A4-85	Polynt	32.90
Drier	Durham Nuodex® Cobalt 6	Venator	0.30
Drier	Durham Nuodex® Zirconium 12	Venator	0.30
Drier	Durham Nuodex® Calcium 5	Venator	0.60
Antiskinning agent	Exkin® 2	Venator	0.10
Solvent	Xylene		15.00
Add components separately while stirring.			

---



---

 100.00
**Specifications**

Vol.-% Anticorrosive pigment reg. pigment/filler	33.2
--	------

Gf-SB03\_002-01\_01B

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.