

in Epoxy ester

Solvent based coatings

Heubach formulation No. 08307

Rev. Number: 01.01

07/08

Function	Product	Producer	PBW
Epoxy ester	WorléeDur D 6311	Worlée-Chemie	39.80
Drier	Octa-Soligen® Calcium 10, basic	Borchers	0.20
Wetting and dispersing agent	SOYA-LECITHIN-CONCENTRATE™ STA	Lubrizol	0.20
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	9.00
Titanium dioxide	KRONOS® 2190	KRONOS	13.05
Magnesium silicate	FINNTALC M15	Elementis	6.10
Muscovite mica	Micro Mica™ W1	Omya	5.25
Calcium/Magnesium carbonate	MICRODOL® EXTRA	Omya	7.85
Grind.			
Rheology modifier	BENTONE® 34, 60% in Exxsol™ D60	Elementis/ExxonMobil	4.00
Drier	Octa-Soligen® Cobalt 6	Borchers	0.15
Drier	Octa-Soligen® Calcium 10, basic	Borchers	0.30
Solvent	Exxsol™ D60	ExxonMobil	10.00
Glycol ether	DOWANOL™ DPM	Dow	3.50
Antiskinning agent	Exkin® 2	Venator	0.60
Add while stirring.			
			100.00

Specifications	
Vol.-% Anticorrosive pigment reg. pigment/filler	20.0
PVC in %	35.0
PVC / CPVC	0.6
Solids in %	68.0

Gf-SB05_002-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.