

## in High solid epoxy

Solvent based coatings

Heubach formulation No. 98160

Rev. Number: 01.01

09/98

Function	Product	Producer	PBW
<b>Component A</b>			
Epoxy resin	D.E.R.™ 671-X75 Epoxy Resin	Olin	21.40
Wetting and dispersing agent	DISPERBYK®-101	BYK-Chemie	0.50
Solvent	Solvesso™ 100	ExxonMobil	1.50
Solvent	Methyl propyl ketone		3.80
<b>Premix.</b>			
Rheology modifier	CAB-O-SIL® TS-720	Cabot	0.70
Silica/Alumina Ceramic	Zeeospheres™ G-400	Zeeosphere Ceramics	15.20
Anticorrosive pigment	HEUCOPHOS® SAPP	Heubach	5.60
Barium sulfate	Sparmite F	Venator	18.00
Iron oxide red pigment	BAYFERROX® 222 FM	LANXESS	5.60
Styrenic hydrocarbon resin	NEVOXY® EPX-L	Neville Chemical	4.50
<b>Grind with a bead mill.</b>			
Epoxy resin	D.E.R.™ 671-X75 Epoxy Resin	Olin	5.40
Solvent	Isopropyl alcohol		1.10
Solvent	Methyl propyl ketone		4.40
<b>Add while stirring.</b>			
			87.70
<b>Component B</b>			
Curing agent	ANCAMIDE® 801	Evonik	8.80
Solvent	Solvesso™ 100	ExxonMobil	1.20
Solvent	Isopropyl alcohol		2.30
<b>Premix and add while stirring.</b>			
			12.30
<b>Mix components A and B thoroughly prior to use.</b>			
			100.00
<b>Specifications</b>			
Solids in %			78.8

Gf-SB06\_003-01\_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.