

## in High solid epoxy

Solvent based coatings

Heubach formulation No. 05261

Rev. Number: 01.01

05/05

Function	Product	Producer	PBW
<b>Component A</b>			
Epoxy resin	EPON™ Resin 828	Hexion	25.80
Rheology modifier	M-P-A® 1078-X	Elementis	0.50
Anticorrosive pigment	HEUCOPHOS® SAPP	Heubach	5.90
Wollastonite	10 AS WOLLASTOCOAT®	NYCO Minerals	2.85
Mg/Al phyllosilicate	Chlorite		8.30
Barium sulfate	Sparmite F	Venator	9.55
Rheology modifier	CAB-O-SIL® TS-720	Cabot	0.60
<b>Grind with a bead mill.</b>			
Reactive diluent	EPODIL® L	Hexion	2.90
Solvent	Super High Flash Naphtha		9.80
Urea resin	CYMEL® U-216-8 resin	Allnex	2.10
Aluminium pigment paste	Aluminium paste L-243	Silberline	10.50
Solvent	Diacetone alcohol		2.00
Solvent	Super High Flash Naphtha		3.90
<b>Add while stirring.</b>			
			84.70
<b>Component B</b>			
Curing agent	ANCAMIDE® 2353	Evonik	15.30
<b>Add while stirring.</b>			
			15.30
<b>Mix components A and B thoroughly prior to use.</b>			
			100.00
<b>Specifications</b>			
Solids in %			79.5

Gf-SB06\_010-01\_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.