

in 2K Polyurethane

Solvent based coatings

Heubach formulation No. 132-16

Rev. Number: 01.01

12/92

Function	Product	Producer	PBW
Component A			
Acrylic polyol	SETALUX® D A 160 X	Allnex	37.70
Solvent	Butyl acetate		5.45
Solvent	Methoxypropyl acetate		5.45
Wetting and dispersing agent	ANTI-TERRA®-204	BYK-Chemie	0.55
Rheology modifier	Efka® RM 1920, 10% in Xylene	BASF	6.60
Premix.			
Rheology modifier	AEROSIL® R 972	Evonik	0.34
Magnesium silicate	FINNTALC M15	Elementis	10.70
Calcium carbonate	Millicarb®	Omya	9.20
Titanium dioxide	KRONOS® 2190	KRONOS	7.80
Anticorrosive pigment	HEUCOPHOS® CAPP	Heubach	9.80
Carbon black pigment	Lamp black® 101	Orion Engineered Carbons	0.01
Grind with a bead mill.			
			93.60
Component B			
Curing agent	Desmodur® N 3390 BA	Covestro	6.40
Add while stirring.			
			6.40
Mix components A and B thoroughly prior to use.			
			100.00
Specifications			
Vol.-% Anticorrosive pigment reg. pigment/filler			22.0
PVC in %			33.4
PVC / CPVC			0.6
Solids in %			67.2

Gf-SB07_001-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.