

in Silicone resin

Solvent based coatings

Evonik Tego formulation No. TBSR P138

Rev. Number: 01.01

03/17

Function	Product	Producer	PBW
Methyl phenyl silicone resin	SILIKOPHEN® P80/X	Evonik	42.50
Wetting and dispersing agent	TEGO® Dispers 670	Evonik	1.00
Rheology modifier	BENTONE® 38	Elementis	0.30
Solvent	Isobutyl alcohol		0.50
Solvent	Butyl glycol acetate		1.20
Defoamer/Deaerator	TEGO® Airex 900	Evonik	0.50
Muscovite mica	MICA TM	Aspanger	17.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	6.00
Copper chromite black spinel	HEUCODUR® Black 9-100	Heubach	6.00
Rheology modifier	AEROSIL® 200	Evonik	0.50
Grind with a bead mill.			
Solvent	Xylene		24.50
Add while stirring.			

100.00

Gf-SB10_011-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.