

in Silicone resin

Solvent based coatings

Evonik Tego formulation No. AC 900 9 002

Rev. Number: 01.01

10/20

Function	Product	Producer	PBW
Methyl phenyl silicone resin	SILIKOPHEN® AC 900	Evonik	40.50
Solvent	Xylene		13.00
Wetting and dispersing agent	TEGO® Dispers 628	Evonik	2.00
Substrate wetting agent	TEGO® Wet 270	Evonik	0.10
Rheology modifier	BENTONE® SD-1	Elementis	1.50
Muscovite mica	MICA TM	Aspanger	16.00
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	5.00
Copper chromite black spinel	HEUCODUR® Black 9-100	Heubach	8.00
Rheology modifier	AEROSIL® R 972	Evonik	1.50
Grind with a bead mill.			
Solvent	Butyl glycol acetate		2.10
Solvent	Xylene		10.30
Add while stirring.			

100.00

Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	13.5
PVC in %	24.8
Solids in %	70.0

Gf-SB10_013-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.