

in Silicone resin

Solvent based coatings

Evonik Tego formulation No. TOP E 900 9 006

Rev. Number: 01.01

10/20

Function	Product	Producer	PBW
Silicone polyester hybrid resin	SILIKOTOP® E 900	Evonik	16.80
Wetting and dispersing agent	TEGO® Dispers 652	Evonik	1.90
Rheology modifier	BENTONE® SD-2	Elementis	0.10
Molecular sieve powder	SYLOSIV® A 3	Grace	0.50
Rheology modifier	AEROSIL® R 972	Evonik	1.20
Carbon black pigment	Colour Black FW 200	Orion Engineered Carbons	0.10
Quartz	SIKRON® SF6000	HPF The Mineral Engineers	1.50
Kaolin	Polsperse™ 50	Imerys	15.20
Anticorrosive pigment	HEUCOPHOS® CAPP	Heubach	6.60
Magnesium silicate	Microtalc™ IT Extra	Elementis	4.40
Titanium dioxide	KRONOS® 2190	KRONOS	14.00
Barium sulfate	EWO	Sachtleben Minerals	15.20
Solvent	Solvesso™ 100	ExxonMobil	5.10
Solvent	Butyl acetate		3.60
Solvent	Xylene		5.80
Grind with a bead mill.			
Catalyst	TIB KAT® 218, 1% in Butyl acetate	TIB Chemicals	1.40
Solvent	Xylene		6.60
Add while stirring.			

100.00

Specifications	
Vol.-% Anticorrosive pigment reg. pigment/filler	14.3
PVC in %	57.4
Solids in %	76.0

Gf-SB10_018-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.