

in Coil coating

Specialty coatings

Heubach formulation No. 140-05

Rev. Number: 01.01

04/93

Function	Product	Producer	PBW
Epoxy resin	EPON™ Resin 1007F	Hexion	25.70
Solvent	Methyl ethyl ketone		15.40
Solvent	Butyl glycol		2.60
Solvent	Solvesso™ 100	ExxonMobil	7.70
Mix until uniform solution prior to addition.			
Solvent	Methyl ethyl ketone		5.50
Solvent	Butyl glycol		0.90
Solvent	Solvesso™ 100	ExxonMobil	2.70
Add while stirring.			
Anticorrosive pigment	HEUCOPHOS® SRPP	Heubach	5.80
Magnesium silicate	MISTRON® MONOMIX G	Imerys	2.65
Titanium dioxide	KRONOS® 2190	KRONOS	9.35
Rheology modifier	AEROSIL® 200	Evonik	0.40
Grind with a bead mill.			
Epoxy resin	EPON™ Resin 1007F	Hexion	8.30
Solvent	Methyl ethyl ketone		5.00
Solvent	Butyl glycol		0.80
Solvent	Solvesso™ 100	ExxonMobil	2.50
Mix until uniform solution prior to addition.			
Melamine resin	CYMEL® 1158 resin	Allnex	4.70
Add while stirring.			
			100.00

Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	35.0
PVC in %	13.9
PVC / CPVC	0.3
Solids in %	56.0

Gf-SC01_002-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.