

## in Aircraft primer

Specialty coatings

Heubach formulation No. 410-10

Rev. Number: 01.01

10/07

Function	Product	Producer	PBW
<b>Component A</b>			
Epoxy resin	Araldite® GT 6071	Huntsman Advanced Materials	18.30
Solvent	Xylene		9.60
Emulsifier	Soya lecithin		0.30
Coalescing agent	DOWANOL™ PMA	Dow	3.20
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® SAPP	Heubach	13.20
Corrosion inhibitor	HEUCORIN® RZ	Heubach	1.50
Magnesium silicate	Microtalc™ IT Extra	Elementis	7.60
Iron oxide yellow pigment	BAYFERROX® 3920	LANXESS	4.50
Titanium dioxide	KRONOS® 2190	KRONOS	3.40
Barium sulfate	Albasoft 70	Sachtleben Minerals	4.90
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	0.10
Rheology modifier	BENTONE® SD-1	Elementis	0.60
<b>Grind with a bead mill.</b>			
Epoxy resin	Araldite® GT 6071	Huntsman Advanced Materials	9.10
Coalescing agent	DOWANOL™ PMA	Dow	4.50
<b>Add while stirring.</b>			
			80.80
<b>Component B</b>			
Curing agent	Aradur® 3776 XW 55	Huntsman Advanced Materials	10.95
Solvent	n-Butyl alcohol		1.20
Solvent	1-Propanol		1.35
Solvent	Solvesso™ 100	ExxonMobil	2.85
Coalescing agent	DOWANOL™ PM	Dow	2.85
<b>Premix and add while stirring.</b>			
			19.20
<b>Mix components A and B thoroughly prior to use.</b>			
			100.00
<b>Specifications</b>			
Vol.-% Anticorrosive pigment reg. pigment/filler			47.0
PVC in %			36.0
CPVC in %			45.0
PVC / CPVC			0.8

Gf-SC02\_003-01\_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.