

## in Wash primer

Specialty coatings

Heubach formulation No. 746-07

Rev. Number: 01.01

04/15

Function	Product	Producer	PBW
Polyvinyl butyral (PVB)	MOWITAL® BA 20 S	Kuraray	10.80
Solvent	n-Butyl alcohol		60.70
Solvent	Xylene		22.10
Mix until uniform solution prior to addition.			
Anticorrosive pigment	HEUCOPHOS® CMP	Heubach	4.60
Magnesium silicate	FINNTALC M15	Elementis	1.40
Rheology modifier	AEROSIL® R 972	Evonik	0.40
Grind with a bead mill.			

---



---

100.00

Specifications	
Vol.-% Anticorrosive pigment reg. pigment/filler	70.0
PVC in %	19.4
PVC / CPVC	0.4
Solids in %	17.2

Gf-SC03\_013-01\_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.