

in Direct to metal

Specialty coatings

Heubach formulation No. 954-05

Rev. Number: 01.01

03/20

Function	Product	Producer	PBW
	Demi. water		8.20
Rheology modifier	ACRYSOL™ RM-5000	Dow	0.50
Wetting and dispersing agent	TEGO® Dispers 750 W	Evonik	0.40
Substrate wetting agent	SURFYNOL® 104 E	Evonik	0.40
Defoamer	BYK®-023	BYK-Chemie	0.20
Neutralizing agent	AMP-90™	ANGUS Chemie	0.20
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	2.35
Titanium dioxide	TIOXIDE® TR92	Venator	12.10
<b>Grind with a bead mill.</b>			
	Demi. water		1.60
Defoamer	BYK®-024	BYK-Chemie	0.15
Styrene acrylic dispersion	Pliotec® HDT12	Synthomer	64.80
Solvent	Mono propylene glycol		1.00
Glycol ether	DOWANOL™ DPM	Dow	0.80
Glycol ether	DOWANOL™ DPnB	Dow	1.20
Coalescing agent	Eastman Optifilm™ Enhancer 300	Eastman Chemical	0.50
Rheology modifier	ACRYSOL™ RM-8W	Dow	0.20
Flash rust inhibitor	HEUCOFLASH™ LQ1	Heubach	0.80
	Demi. water		4.60
<b>Add while stirring.</b>			

100.00

Adjust pH 8.5 with ammonia, 25%.

### Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	20.0
PVC in %	11.2
PVC / CPVC	0.2
Solids in %	46.9

Gf-SC04\_019-01\_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.