

in UV cured system

Specialty coatings

Bayer formulation No. FWO 4061

Rev. Number: 01.01

08/10

Function	Product	Producer	PBW
Urethane acrylate	DESMOLUX® XP 2740	Allnex	26.30
Anticorrosive pigment	HEUCOPHOS® ZPA	Heubach	2.60
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.25
Magnesium silicate	Microtalc™ IT Extra	Elementis	13.15
Tripropylene glycol diacrylate	TPGDA®	Allnex	21.05
Grind to a fineness of < 10 microns.			
Adhesion promoter	EBECRYL® 168	Allnex	5.40
Pigment red paste	Pinova Red HP 1070	Pinova	3.50
Tripropylene glycol diacrylate	TPGDA®	Allnex	11.90
Acrylic resin	Photomer® 4039	iGM RESINS	11.90
Photoinitiator	Irgacure® TPO-L	BASF	1.05
Photoinitiator	Darocur® 1173	BASF	2.90
Add while stirring.			

100.00

Gf-SC05_002-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.