

in Powder coating

Specialty coatings

Heubach formulation No. 03248

Rev. Number: 01.01

05/03

Function	Product	Producer	PBW
Polyester resin	Uralac® P 846	DSM Coating Resins	65.30
Crosslinker	Primid® QM-1260	EMS-CHEMIE	3.45
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	5.00
Nickel antimony titanium yellow	HEUCODUR® Yellow 152	Heubach	0.06
Chrome antimony titanium buff	HEUCODUR® Yellow 252	Heubach	0.02
Barium sulfate	BLANC FIXE™ N	Venator	16.55
Titanium dioxide	KRONOS® 2160	KRONOS	8.35
Carbon black pigment	Colour Black FW 200	Orion Engineered Carbons	0.02
Flow and levelling agent	Resiflow® PV 5	Estron Chemical	1.00
Degassing agent	Benzoin		0.25
Add.			
			100.00

Specifications	
PVC in %	10.4

Gf-SC06_001-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.