

## in Powder coating

Specialty coatings

Heubach formulation No. 590-04

Rev. Number: 01.01

11/10

Function	Product	Producer	PBW
Polyester resin	Uralac® P 885	DSM Coating Resins	65.30
Crosslinker	Primid® XL-552	EMS-CHEMIE	3.45
Anticorrosive pigment	HEUCOPHOS® SAPP	Heubach	5.00
Nickel antimony titanium yellow	HEUCODUR® Yellow 152	Heubach	0.06
Chrome antimony titanium buff	HEUCODUR® Yellow 252	Heubach	0.02
Carbon black pigment	Colour Black FW 200	Orion Engineered Carbons	0.02
Titanium dioxide	KRONOS® 2310	KRONOS	8.35
Barium sulfate	BLANC FIXE™ F	Venator	15.80
Degassing agent	Ceridust® 9615 A	Clariant	1.00
Flow control agent	Resiflow® PV-88	Estron Chemical	1.00
Add.			

---



---

100.00

**Gf-SC06\_005-01\_01A**

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.