

## in Alkyd emulsion

Water based coatings

Heubach formulation No. 881-07

Rev. Number: 01.01

03/18

Function	Product	Producer	PBW
Alkyd emulsion	RESYDROL® AZ 436w/45WA	Allnex	55.30
Neutralizing agent	Ammonia, 10%		1.00
Wetting agent	Borchi® Gen 1253	Borchers	2.95
Defoamer	Borchers® AF 1171	Borchers	0.30
	Demi. water		13.10
<b>Premix.</b>			
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	5.50
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.60
Magnesium silicate	FINNTALC M05N	Elementis	8.10
Calcium carbonate	DURCAL 2	Omya	5.30
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	6.40
<b>Grind with a bead mill.</b>			
Rheology modifier	Borchi® Gel 0626	Borchers	1.00
Catalyst	Borchi® OXY - Coat 1101	Borchers	0.15
Neutralizing agent	AMP-90™	ANGUS Chemie	0.30
<b>Add while stirring.</b>			

100.00

Adjust pH 8.5 - 9.3 with ammonia.

### Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	22.0
PVC in %	25.9
PVC / CPVC	0.5
Solids in %	50.0

Gf-WB01\_018-01\_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.