

in Hybrid resin

Other water based coatings

NYCO Minerals formulation

Rev. Number: 01.01

10/99

Function	Product	Producer	PBW
	Demi. water		8.65
Rheology modifier	CELLOSIZETM QP 4400H	Dow	0.15
Dispersing agent	TAMOLTM 165A Dispersant	Dow	1.60
Add components separately while stirring.			
Surfactant	IGEPAL® CTA-639/W	SOLVAY	0.10
Defoamer	Patcote® 519	Hydrite Chemical	0.10
Add while stirring.			
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	13.50
Wollastonite	10 ES WOLLASTOCOAT®	NYCO Minerals	10.60
Titanium dioxide	Ti-Pure™ R-900	The Chemours Company	4.00
Chromium oxide green pigment	COLORTHERM® Green GN-M	LANXESS	7.90
Grind.			
	Demi. water		2.65
Add while stirring.			
Solvent	Butyl CELLOSOLVE™ Solvent	Dow	2.85
Solvent	DALPAD™ A	Dow	0.35
Acrylic dispersion	RHOPLEX™ WL-91	Dow	15.50
Mix until uniform solution prior to addition.			
Polyester polyurethane disp.	NeoRez® R-961	DSM Coating Resins	32.05
Add while stirring.			
			100.00
Specifications			
PVC in %			28.0

Gf-OW08_001-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.