

in Hybrid resin

Other water based coatings

DSM Coating Resins formulation No. D-1515

Rev. Number: 01.01

03/00

Function	Product	Producer	PBW
Styrene acrylic dispersion	NeoCryl® XK-85	DSM Coating Resins	10.90
	Demi. water		6.15
Defoamer	Drew™ 210-693	Ashland	0.15
Dispersing agent	NUOSPERSE® W-33	Elementis	1.30
Rheology modifier	ACRYSOL™ TT-935, 50% in demi. water	Dow	0.60
Corrosion inhibitor	NALZIN® FA 179	Elementis	0.50
Solvent	Butyl glycol		2.10
Acrylic emulsion	NeoCryl® BT-24	DSM Coating Resins	2.50
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	6.30
Talc/chlorite filler	LUZENAC 20M0	Imerys	10.50
Iron oxide black pigment	BAYFERROX® 318 M	LANXESS	4.10
Carbon black pigment	Special Black® 4	Orion Engineered Carbons	0.50
Rheology modifier	AEROSIL® R 972	Evonik	0.50
Grind to a fineness of < 20 microns, temperature < 40 °C.			
Styrene acrylic dispersion	NeoCryl® XK-85	DSM Coating Resins	43.00
	Demi. water		1.00
Coalescing agent	Eastman Texanol™	Eastman Chemical	1.10
Corrosion inhibitor	NACORR® 1652	King Industries	1.90
Add grind while stirring.			
Epoxy ester	RESYDROL® AX 237w/70BG	Allnex	4.45
Solvent	Butyl glycol		2.10
Drier	Octa-Soligen® Cobalt 10	Borchers	0.05
Neutralizing agent	Ammonia, 25%		0.30
Premix and let stay the solution overnight before addition.			
			100.00
Specifications			
PVC in %			22.0
Solids in %			49.0

Gf-OW08_003-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.