

in 1K Polyurethane

Water based coatings

Heubach formulation No. 246-08

Rev. Number: 01.01

10/00

Function	Product	Producer	PBW
Polyurethane resin	Halwedrol® OX 48/40 W	DSM Coating Resins	33.70
Wetting and dispersing agent	DISPERBYK®-184	BYK-Chemie	1.00
Defoamer	FoamStar® ED 2526	BASF	0.60
Defoamer	BYK®-020	BYK-Chemie	0.60
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	9.30
Corrosion inhibitor	HEUCORIN® RZ	Heubach	1.00
Talc/chlorite filler	LUZENAC 10M2	Imerys	7.30
Mica/quartz/chlorite filler	Plastorit® Micro	Imerys	4.90
Titanium dioxide	SACHTLEBEN R-KB-6	Venator	14.65
Rheology modifier	AEROSIL® R 972	BASF	0.50
Grind to a fineness of app. 20 microns.			
Drier	Nuodex® WEB Combi AQ	Venator	0.65
Solvent	Butyl glycol		0.65
Premix and add while stirring.			
	Demi. water		5.10
Polyurethane resin	Halwedrol® OX 48/40 W	DSM Coating Resins	17.10
Solvent	Butyl glycol		0.50
Flash rust inhibitor	CHE®-COAT-CI L8AF	C.H. Erbslöh	0.20
Flash rust inhibitor	CHE®-COAT-CI L8NF	C.H. Erbslöh	0.20
Antiskinning agent	Exkin® 2	Venator	0.20
Wetting agent	TROYSOL™ LAC	Troy Chemical	0.40
Add components separately while stirring.			
	Demi. water		0.95
Rheology modifier	Viscalex® HV30	BASF	0.25
Neutralizing agent	Dimethylethanolamine		0.05
Mix until uniform paste prior to addition.			
Rheology modifier	Rheovis® PU 1280	BASF	0.10
Solvent	Butyl glycol		0.10
Premix and add while stirring.			

 100.00
Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	22.3
PVC in %	35.1
PVC / CPVC	0.6
Solids in %	60.0

Gf-WB03_003-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.