

in 1K Polyurethane

Water based coatings

Heubach formulation No. 548-06

Rev. Number: 01.01

04/10

Function	Product	Producer	PBW
Polyurethane dispersion	Bayhydrol® UH XP 2592	Covestro	28.90
Solvent	Butyl glycol		1.70
Glycol ether	DOWANOL™ DPnB	Dow	1.70
Antiskinning agent	Ascinin® Anti Skin 0445	Borchers	0.10
Premix.			
Drier	Nuodex® WEB Combi AQ	Venator	1.25
	Demi. water		1.25
Add while stirring.			
Defoamer	BYK®-022	BYK-Chemie	0.15
Anticorrosive pigment	HEUCOPHOS® ZAM-PLUS	Heubach	10.80
Grind 5 minutes.			
	Demi. water		3.25
Add.			
Neutralizing agent	N-Ethyl-diisopropylamine		0.25
	Demi. water		0.25
Premix and add while stirring.			
Magnesium silicate	FINNTALC M05N	Elementis	3.95
Calcium/Magnesium carbonate	MICRODOL® SUPER	Omya	6.50
Titanium dioxide	SACHTLEBEN R-KB-6	Venator	10.20
Carbon black pigment	PRINTEX® 55	Orion Engineered Carbons	0.10
Rheology modifier	AEROSIL® 300	Evonik	0.30
Grind to a fineness of < 20 microns, temperature < 40 °C.			
Polyurethane dispersion	Bayhydrol® UH XP 2592	Covestro	28.90
Add to the grind.			
Rheology modifier	Borchi® Gel PW 25	Borchers	0.05
	Demi. water		0.30
Premix and add while stirring.			
Surfactant	BYK®-346	BYK-Chemie	0.10
Add while stirring.			

100.00

Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	33.0
PVC in %	29.0
PVC / CPVC	0.5
Solids in %	58.0

Gf-WB03_010-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.