## **HEUCOPHOS® CMP**



## in 1K Polyurethane

Grind with a bead mill.

Rheology modifier Add while stirring.

Water based coatings	Heubach formulation No. 714-04	Rev. Number: 01.01	01/14
Function	Product	Producer	PBW
Polyurethane dispersion	DAOTAN® VTW 1250/40WA	Allnex	68.60
Neutralizing agent	Ammonia, 10%		0.75
Substrate wetting agent	SURFYNOL® SE-F	Evonik	0.30
Defoamer	ADDITOL® VXW 4973	Allnex	0.45
	Demi. water		6.95
Premix.			
Anticorrosive pigment	HEUCOPHOS® CMP	Heubach	4.40
Magnesium silicate	FINNTALC M05N	Elementis	6.00
Calcium carbonate	Omyacarb® 2	Omya	4.05
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	5.00
Rheology modifier	Borchi® Gel L 75 N, 10% in demi. water	Borchers	1.75

100.00

1.75

Adjust pH 8.0 - 8.5 with ammonia, 10%.		
Specifications		
Vol% Anticorrosive pigment reg. pigment/filler		
PVC in %		
PVC / CPVC	0.5	

Borchi® Gel L 75 N, 10% in demi. water | Borchers

Gf-WB03\_012-01\_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.