

in Styrene acrylic dispersion

Water based coatings

Heubach formulation No. 03252

Rev. Number: 01.01

05/03

Function	Product	Producer	PBW
Styrene acrylic dispersion	NeoCryl® XK-85	DSM Coating Resins	11.75
	Demi. water		2.90
Defoamer	Drewplus™ TS-4380	Ashland	0.05
Wetting and dispersing agent	NUOSPERSE® W-22	Elementis	1.35
Rheology modifier	Borchi® Gel L 75 N, 50% in demi. water	Borchers	0.85
Corrosion inhibitor	NALZIN® FA 179	Elementis	0.55
Solvent	Butyl glycol		1.75
Styrene acrylic dispersion	NeoCryl® A-1094	DSM Coating Resins	2.35
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	8.65
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.95
Magnesium silicate	FINNTALC M10	Elementis	8.15
Titanium dioxide	KRONOS® 2190	KRONOS	7.70
Carbon black pigm. preparation	Hostatint® Black GR 30	Clariant	0.95
Grind to a fineness of app. 20 microns.			
Styrene acrylic dispersion	NeoCryl® XK-85	DSM Coating Resins	47.00
Solvent	Butyl glycol		2.65
Coalescing agent	Eastman Texanol™	Eastman Chemical	1.20
Defoamer	FoamStar® SI 2213	BASF	1.20
Add grind while stirring.			
			100.00
Adjust pH 9.0 with ammonia, 25%.			
Specifications			
PVC in %			26.6
Solids in %			52.8

Gf-WB06_011-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.