

in Styrene acrylic acid ester dispersion

Water based coatings

Heubach formulation No. 339-06

Rev. Number: 01.01

06/04

Function	Product	Producer	PBW
	Demi. water		8.60
Defoamer	BYK®-044	BYK-Chemie	0.10
Neutralizing agent	AMP-90™	ANGUS Chemie	0.15
Dispersing agent	NUOSPERSE® FX 600	Elementis	0.55
Wetting and dispersing agent	NUOSPERSE® FN 265	Elementis	0.35
Defoamer	ADDITOL® VXW 4973	Allnex	0.35
Corrosion inhibitor	NALZIN® FA 179	Elementis	0.15
Preservative	Mergal® K10N	Troy Chemical	0.20
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	5.05
Corrosion inhibitor	HEUCORIN® RZ	Heubach	0.55
Magnesium silicate	Microtalc™ IT Extra	Elementis	5.00
Calcium carbonate	Millicarb®	Omya	3.15
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	4.30
Grind with a bead mill.			
Rheology modifier	DSX® 1550	BASF	0.20
Add to the grind.			
Styrene acrylic acid ester disp.	Mowilith® LDM 7411	Celanese	48.70
Neutralizing agent	Ammonia		0.20
	Demi. water		21.00
Coalescing agent	Eastman Texanol™	Eastman Chemical	1.40
Premix while stirring. Then add grind.			
			100.00

Specifications	
Vol.-% Anticorrosive pigment reg. pigment/filler	26.7
PVC in %	19.1
PVC / CPVC	0.4
Solids in %	43.8

Gf-WB06_016-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.