

in Butyl styrene acrylic dispersion

Water based coatings

Heubach formulation No. 567-17

Rev. Number: 01.01

03/10

Function	Product	Producer	PBW
Butyl styrene acrylic dispersion	Acronal® LR 8977	BASF	48.65
Defoamer	BYK®-022	BYK-Chemie	0.25
Substrate wetting agent	SURFYNOL® 104 PA	Evonik	0.40
Premix.			
	Demi. water		7.10
Surfactant	Lutensit® A-EP	BASF	0.10
Neutralizing agent	Ammonia		0.30
Premix and add while stirring.			
Solvent	Solvenon® PP	BASF	0.75
Solvent	Exxsol™ D60	ExxonMobil	0.75
Solvent	Butyl glycol		0.75
Add while stirring.			
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	11.85
Corrosion inhibitor	HEUCORIN® RZ	Heubach	1.30
Talc/chlorite filler	LUZENAC 20M2	Imerys	14.85
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	11.00
Grind with a bead mill.			
Defoamer	BYK®-022	BYK-Chemie	0.15
Add while stirring.			
Flash rust inhibitor	CHE®-COAT-CI LNFA4	C.H. Erbslöh	0.55
	Demi. water		0.55
Premix and add while stirring. Adjust pH 9.0 - 9.5 with ammonia.			
Rheology modifier	Rheovis® PU 1280	BASF	0.35
Solvent	Butyl glycol		0.35
Premix and add while stirring.			
			100.00
Specifications			
Vol.-% Anticorrosive pigment reg. pigment/filler			26.6
PVC in %			33.1
PVC / CPVC			0.6

Gf-WB06_031-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.