

## in Styrene acrylic dispersion

Water based coatings

Synthomer formulation No. WB ACP 10

Rev. Number: 01.01

10/13

Function	Product	Producer	PBW
	Demi. water		14.00
Rheology modifier	ACRYSOL™ RM-5000	Dow	0.50
<b>Add in order under stirring.</b>			
Wetting and dispersing agent	TEGO® Dispers 750 W	Evonik	0.50
Substrate wetting agent	SURFYNOL® 104 E	Evonik	0.40
Neutralizing agent	AMP-90™	ANGUS Chemie	0.20
Defoamer	BYK®-023	BYK-Chemie	0.20
<b>Mix well and add under stirring.</b>			
Anticorrosive pigment	HEUCOPHOS® ZCP-PLUS	Heubach	8.00
Magnesium silicate	PLUSTALC™ D30E	Elementis	6.00
Titanium dioxide	TIOXIDE® TR92	Venator	8.00
Barium sulfate	BLANC FIXE™ N	Venator	6.00
Iron oxide black pigment	BAYFERROX® 316	LANXESS	0.35
<b>Disperse at high speed then add.</b>			
Styrene acrylic dispersion	Pliotec® HDT12	Synthomer	50.00
Coalescing agent	DOWANOL™ DPM	Dow	0.90
Coalescing agent	DOWANOL™ DPnB	Dow	1.00
Coalescing agent	Eastman Optifilm™ Enhancer 300	Eastman Chemical	0.50
<b>Mix well then add under medium shear.</b>			
	Demi. water		2.45
Rheology modifier	ACRYSOL™ RM-8W	Dow	0.20
Flash rust inhibitor	AB RUST® A4	Laboratoires LABEMA	0.80
			100.00

### Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	28.8
PVC in %	19.0
Solids in %	47.1

Gf-WB06\_033-01\_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.