

in Styrene acrylic dispersion

Water based coatings

Heubach formulation No. 940-04

Rev. Number: 01.01

06/19

Function	Product	Producer	PBW
Styrene acrylic dispersion	Acronal® PRO 7600	BASF	40.55
Defoamer	FoamStar® SI 2210	BASF	0.20
	Demi. water		5.85
Dispersing agent	Hydropalat® WE 3425	BASF	0.05
Neutralizing agent	Ammonia, 25%		0.55
Premix.			
Coalescing agent	DOWANOL™ PPh	Dow	0.70
Solvent	Exxsol™ D60	ExxonMobil	0.70
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	7.75
Magnesium silicate	Talc LP30	LITHOS Industrial Minerals	3.40
Zinc sulfide/Barium sulfate	Lithopone 30% L	Venator	12.15
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	8.10
Grind with a bead mill.			
Styrene acrylic dispersion	Acronal® PRO 7600	BASF	17.15
Defoamer	FoamStar® SI 2210	BASF	0.20
Add to the grind.			
Flash rust inhibitor	CHE®-COAT-CI LNFA4	C.H. Erbslöh	0.20
	Demi. water		0.20
Premix and add while stirring.			
Rheology modifier	Rheovis® PU 1280	BASF	0.40
Solvent	Butyl glycol		1.30
Premix and add while stirring.			
Neutralizing agent	Ammonia, 25%		0.55
Add to the grind.			
			100.00
Adjust pH 9.3 - 9.5 with ammonia, 25%.			
Specifications			
Vol.-% Anticorrosive pigment reg. pigment/filler			28.0
PVC in %			23.3
PVC / CPVC			0.4
Solids in %			60.3

Gf-WB06_048-01_01A

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.