

in Direct to metal

Specialty coatings

Heubach formulation No. 964-05

Rev. Number: 01.02

09/23

Function	Product	Producer	PBW
	Demi. water		9.50
Wetting and dispersing agent	EDAPLAN® 490	MÜNZING	1.20
Neutralizing agent	AMP-90™	ANGUS Chemie	0.05
Defoamer	BYK®-024	BYK-Chemie	0.10
Anticorrosive pigment	HEUCOPHOS® CMP	Heubach	2.10
Titanium dioxide	KRONOS® 2190	KRONOS	12.10
Grind with a bead mill.			
Acrylic dispersion	ALBERDINGK® AC 2403	Alberdingk Boley	71.00
Defoamer	BYK®-024	BYK-Chemie	0.10
Surfactant	BYK®-349	BYK-Chemie	0.30
Coalescing agent	Eastman Optifilm™ Enhancer 300	Eastman Chemical	2.00
Flash rust inhibitor	HEUCOFLASH™ LQ1	Heubach	0.75
Rheology modifier	TAFIGEL® PUR 60,10%BG/d.water10:80	MÜNZING	0.80
Add while stirring.			

 100.00

Adjust pH 8.5 - 9.5 with AMP 90.

Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	20.0
PVC in %	10.8
PVC / CPVC	0.2
Solids in %	47.6

Gf-SC04_021-01_02

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.