

## in 2K Ketac resin

Other solvent based coatings

Heubach formulation No. 1065-10

Rev. Number: 01.01

04/24

Function	Product	Producer	PBW
<b>Component A</b>			
Acetoacetate polyester resin	SETAL® 7205 BA-86	Allnex	15.05
Solvent	Butyl acetate		12.95
Wetting and dispersing agent	ADDITOL® VXW 6208/60	Allnex	1.55
Flow agent and defoamer	ADDITOL® XL 123 N	Allnex	0.45
Anticorrosive pigment	HEUCOPHOS® ZPO	Heubach	12.60
Magnesium silicate	FINNTALC M15	Elementis	12.60
Iron oxide yellow pigment	BAYFERROX® 3910	LANXESS	0.30
Titanium dioxide	KRONOS® 2190	KRONOS	19.05
Barium sulfate	EWO	Sachtleben Minerals	2.80
Iron oxide black pigment	BAYFERROX® 320	LANXESS	0.90

Grind with a bead mill until 25 - 30 microns.

78.25

<b>Component B</b>			
Ketimine resin	SETALUX® 7006 SS-65	Allnex	21.75
Add.			

21.75

Mix components A and B thoroughly prior to use.

100.00

<b>Specifications</b>	
Vol.-% Anticorrosive pigment reg. pigment/filler	25.7
PVC in %	35.0
PVC / CPVC	0.6
Solids in %	76.5
Crosslinking in %	125.0

Gf-OS11\_013-01\_01

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.