

in 1K Polyurethane

Water based coatings

Heubach formulation No. 1049-13

Rev. Number: 01.01

05/24

Function	Product	Producer	PBW
Polyurethane dispersion	DAOTAN® TW 1250/39WAMPP	Allnex	64.90
Neutralizing agent	Ammonia, 25%		0.30
Neutralizing agent	AMP-90™	ANGUS Chemie	0.20
	Demi. water		7.50
Substrate wetting agent	SURFYNOL® SE-F	Evonik	0.30
Defoamer	ADDITOL® XW 372 N	Allnex	0.40
Premix.			
Anticorrosive pigment	HEUCOPHOS® ZMP	Heubach	6.95
Magnesium silicate	FINNTALC M05N	Elementis	6.60
Calcium carbonate	DURCAL 2	Omya	3.10
Iron oxide red pigment	BAYFERROX® 130 M	LANXESS	7.55
Drier	ADDITOL® dry CF100	Allnex	0.20
Grind with a bead mill.			
Rheology modifier	Borchi® Gel L 75 N, 1:5 in demi. water	Borchers	2.00
Add while stirring.			

 100.00
Specifications

Vol.-% Anticorrosive pigment reg. pigment/filler	28.3
PVC in %	24.2
PVC / CPVC	0.5
Solids in %	50.6

Gf-WB03_016-01_01

Our application information and any other information in this document as well as our product specifications are based on our current state of knowledge at the Revision Date mentioned in the respective document. They are non-binding and cannot be taken as a guarantee. The processing company must establish the suitability of individual products itself. As their use lies beyond our knowledge and control, we cannot accept any liability relating to the use of our products in particular applications. In addition to that, the legal rights of third parties must always be considered. The product specification agreed between the customer and ourselves is the basis upon which our general sales and delivery conditions are set and is the deciding factor concerning any liabilities. Our standard specification is then valid if no specification has been agreed upon between the customer and ourselves.